

# Mortar for Production Lightweight Block

## M220B



### Product Characteristics

Ready - mixed mortar for production of Lightweight block (Cellular Lightweight Concrete: CLC) by mixing with foaming agent and water according to the ratio precribed.

### How to prepare

- Mix TPI M220B 1 bag (50kg) with 7.0 Liters of water and mix well
- Add foaming agent according to the ratio of the manufacturer and mix until mixture it homogeneous. After that pour the mixture into the mold.
- Let the mortar set for about 2 hours, then remove the block out of mold before cutting to the required size.



### Usage Quantities ( For production Lightweight block size 20x60x7.5 cm )

Number of bags (bag)	Amount of mortar (kg)	Number of Lightweight block production (Pieces)
20	1.000	120

Suitable for production Lightweight block (Cellular Lightweight Concrete : CLC)